



## POLYCARBONATE MAINTENANCE

### **Preliminary Remarks**

Thanks to improved UV-protection, sheet eliminates all ageing phenomena. The sheets retain their original appearance after long-term exposure to sunlight. Decrease of light transmission and loss of brilliance are reduced to a minimum. Thanks to the self-cleaning effect, maintenance of polycarbonate UV sheets compared to standard polycarbonate sheets is reduced.

### **Warranty**

Because of their improved properties Makrolon® Mono Longlife sheets have a warrant of 10 years on weather ability and on impact strength. Contact us for more information.

### **Cleaning**

Polycarbonate UV sheet can be cleaned by washing with a soft sponge and lukewarm water containing a mild soap. Rinse well afterwards with clean water and dry with a chamois leather. A subsequent anti-static treatment is recommended. There are commercially available products which act at the same time as a cleaning and anti-static agent. Ethyl alcohol, isopropyl alcohol and petroleum ether (boiling point 65°C) are for removing fresh paint splashes, grease etc. Wash and rinse thoroughly afterwards as described above. Do not use abrasive or highly alkaline cleaners, acetone, benzene, leaded petroleum or carbon tetrachloride.